

NEARFINISH LPS

Shiny Effect without press By mechanical polishing with balls

Garments should be free from any finishing agent,
If necessary treat the garments with bio-polish enzyme to make the surface smooth,
then dry.

Prepare a solution composed of:
800 g/l NEARFINISH LPS
Colour with NEARSTONE pigments,
For example, black:
20 g/l NEARSTONE BLACK D-B

Spray about 50% of the garments weight, i.e. 300ml for a 600g garment.

Put the garment on inflatable mannequin

- Spray one first layer (150ml), make smooth with a brush, allow to dry (if necessary in an oven at 50°C)
- Repeat a second time.
- Cure at 140°C for 10 minutes.

Treat the garment in warm tumble drier with heavy, hard, smooth balls to get the shiny effect.

